



APPLICATION ANWENDUNG / APPLICATION / TOEPASSING / APLICACIÓN / APPLICAZIONE	LANDSCAPING
PRODUCTION METHOD HERSTELLUNGSVERFAHREN / MODE DE FABRICATION / PRODUCTIEPROCÉS PROCESO DE FABRICACIÓN / PROCESSI DI FABBRICAZIONE	TUFTED
FIBRE FASER / FIBRE / VEZEL / FIBRA / FIBRA	PE DTEX 8000
PILE HEIGHT POLHÖHE / HAUTEUR DU VELOURS / POOLHOOGTE / ALTURA DE LA PILA / ALTEZZO FELPA	±42 MM
TOTAL HEIGHT GESAMTHÖHE / HAUTEUR TOTALE / TOTALE HOOGTE / ALTURA TOTAL / ALTEZZO TOTALE	±44 MM
PILE WEIGHT POLEINSATZGEWICHT / POIDS DU VELOURS / POOLGEWICHT / PESO DE LA PILA / PESO FELPA	± 1210 GR/M²
TOTAL WEIGHT GESAMTGEWICHT / POIDS TOTAL / TOTAALGEWICHT / PESO TOTAL / PESO TOTALE	± 2530 GR/M²
GAUGE TUFTTEILUNG / JAUGE / TUFTDELING / GALGA / SCARTAMENTO	3/8"
STITCHES (10 CM¹) STICHZAHL / NOMBRE DE POINTS / STEKENAANTAL / PUNTADAS / SERRAGGIO PUNTI	± 17 /10CM¹
STITCHES (M²) STICHZAHL / NOMBRE DE POINTS / STEKENAANTAL / PUNTADAS / SERRAGGIO PUNTI	± 17800 /M²
PRIMARY BACKING TRÄGER / DOSSIER PRIMAIRE / TUFTDOEK / BACKING PRINCIPAL / SUPPORTO PRIMARIO	PP 186 GR/M²
SECONDARY BACKING RÜCKEN / DOSSIER SECONDAIRE / SECUNDAIRE BACKING / BACKING SECUNDARIO / SUP- PORTO SECONDARIO	LATEX ±1134 GR/M²
WATER PERMEABILITY WASSERDURCHLASSIGKEIT / PERMÉABILITÉ / WATERDOORLATENDHEID / PERMEABILIDAD AL AGUA / PERMEABILITÀ ACQUA	60 L/MIN/M²
UV-WARRANTY NORTH EUROPE ABOVE PARIS, SOUTH EUROPE BELOW PARIS UV-GARANTIE / GARANTIE UV / UV GARANTIE / GARANTÍA UV / GARANZIA UV	NORTH EUROPE: 7 YEARS / SOUTH EUROPE: 5 YEARS
ROLL WIDTH ROLLBREITE / LARGEUR DES ROULEAUX / ROLBREDTE / ANCHO DE ROLLO / LARGHEZZA ROTOLO	2 M / 4 M
ROLL LENGTH ROLLÄNGE / LONGUEUR DES ROULEAUX / ROLLENGTE / LARGO DEL ROLLO / LUNGHEZZA ROTOLO	±25 M
INFILL SAND FÜLLSAND / SABLE DE REMPLISSAGE / INSTROOIZAND LA ARENA DE SÍLICE / SABBIA SILICEA	8-10 KG/M²

